



Advantage Semi Extensible

Benefits

- High Tensile Energy Absorption (TEA)
- Excellent runnability
- Advantage SE is also available in wet strength quality.

End-uses

- We particularly recommend its use for pasted valve bags for powdered substance and when high strength and best conversion properties are required.



Management Systems / Certifications		Food Contact Approvals
ISO 9001:2015 ISO 14001:2015 ISO 45001:2018 EN 15593:2008 / BRCGS:	PEFC-CoC, FSC-CoC FSC-CW;	German BFR Recommendation XXXVI Code of Federal Regulations, Food and Drugs (FDA), 21 CFR Ch.I (1. April 2019) Source Reduction Council of CONEG

Technical Values									
Properties		Method		Typical values (please select the 2-10 most common grammages)					
Basis Weight	g/m ²	ISO 536		70	75	80	85	90	100
Tensile strength	kN/m	ISO 1924-3	md cd	5.6 4.1	6.0 4.4	6.4 4.6	6.8 4.9	7.2 5.2	8.0 5.8
Tensile Index	Nm/g	ISO 1924-3	md cd	80 58	80 58	80 58	80 58	80 58	80 58
Stretch at break	%	ISO 1924-3	md cd	5.8 7.4	5.8 7.4	5.8 7.4	5.8 7.4	5.8 7.4	5.8 7.4
Tensile Energy Absorption (TEA)	J/m ²	ISO 1924-3	md cd	200 200	215 215	230 230	245 245	260 260	290 290
TEA Index	J/g	ISO 1924-3	md cd	2.9 2.9	2.9 2.9	2.9 2.9	2.9 2.9	2.9 2.9	2.9 2.9
Tear Index	mN.m ² /g	ISO 1974	md cd	10.5 11.5	10.5 11.5	10.5 11.5	10.5 11.5	10.5 12.0	10.5 12.0
Air Resistance (Gurley)	s	ISO 5636-5		15	15	15	15	15	15
Cobb ₆₀	g/m ²	ISO 535		32	32	32	32	32	32
The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.									

	Issued from 01.01.2021, latest version available on www.mondigroup.com	Test conditions: ISO 187 : 1990 (23°C ± 1 C/RH 50% ±2)
--	--	---