

Advantage MF White Pulp Wrapping



Benefits

- Pure unbleached virgin kraft fibre
- Very high strength properties
- High stretch

End-uses

- Wrapping bales of bleached pulp



Management Systems / Certifications		Food Contact Approvals
ISO 9001:2015 ISO 14001:2015 ISO 45001:2018 EN 15593:2008	PEFC-CoC FSC-CoC FSC-CW	German BFR Recommendation XXXVI Code of Federal Regulations, Food and Drugs (FDA), 21 CFR Ch.I (1. April 2019) Source Reduction Council of CONEG

Technical Values						
Properties		Method		Typical values		
Basis Weight	g/m ²	ISO 536		130	140	150
Tensile strength	kN/m	ISO 1924-3	md cd	9,8 6,8	10,5 7,3	11,3 7,8
Tensile Index	Nm/g	ISO 1924-3	md cd	75 52	75 52	75 52
Stretch at break	%	ISO 1924-3	md cd	8,8 8,8	8,8 8,8	8,8 8,8
Tear Index	mN.m ² /g	ISO 1974	md cd	15,0 20,0	16,0 20,0	17,0 20,0
Bursting Strength	kPa	ISO 2758		800	850	900
Air Resistance	s	ISO 5636-5		20	20	20
Cobb-60''	g/m ²	ISO 535		30	30	30

The table above shows typical values for certain basis weights.

The applied testing method standards always refers to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.

	SPECIALITYWORLD by mondi	Issued from 01.01.2021 latest version available on www.mondigroup.com	Testing conditions: ISO 187:1990 (23 °C ± 1°C / RH 50% ± 2%)
--	------------------------------------	---	--