



Advantage eCom Kraft

Benefits

- Natural look and feel
- 100% fresh fibre
- High strength properties
- High tear-resistance
- High stiffness
- Excellent runnability

End-uses

- Mailer bags
- eCom FFS
- eGrocery bags



PEFC	FSC*	Food Contact Approvals	Quality Management System	Environmental Management System	Safety Management System
•	•	BfR XXXVI FDA Regulation §§ 176.170 FDA Regulation §§ 176.180	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

*on demand

Technical Values

Properties		Method	Typical values					
Basis Weight	g/m ²	ISO 536	70	80	90	100	110	120
Thickness**	µm	ISO 534	110	120	135	145	165	175
Tensile strength MD	kN/m	ISO 1924-3	7,7	8,8	9,9	11,0	12,1	13,2
Tensile strength CD	kN/m	ISO 1924-3	4,2	4,8	5,4	6,0	6,6	7,2
Tear strength MD	mN	ISO 1974	910	1040	1170	1300	1430	1620
Tear strength CD	mN	ISO 1974	910	1040	1260	1400	1595	1680
Cobb ₆₀	g/m ²	ISO 535	32	32	32	32	32	32
Burst strength	kPa	ISO 2758	350	400	450	500	550	600
Roughness Bendtsen TS**	ml/min	ISO 8791-2	1000	1050	1150	1300	1450	1700
Stretch MD	%	ISO 1924-3	2,6	2,6	2,6	2,6	2,6	2,6
Density**	kg/m ³		645	665	690	690	665	685

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.

** Average values, not specified

Issued from 01.07.2022,
latest version available on
www.mondigroup.com

Test conditions:
ISO 187:1990
(23 C + 1 C/RH 50% +2)