



## EcoVantage Light Fashion

### Benefits

- High Sustainable approach
- Full recycled fibre image
- Recycled fibres from 100% of pre-consumer and post-consumer waste
- Enhanced performance paper with the highest recycled content
- Stable shade appearance
- Reasonable strength and printability

### End-uses

- Shopping bag with focus for fashion sector
- Small sized shopping bags
- Home delivery service



PEFC	FSC*	BRCGS	Quality Management System	Environmental Management System	Safety Management System
•	•	Packaging and Packaging materials	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

\*on demand

### Technical Values

Properties		Method	Typical values						
			70	80	90	100	110	115	120
Basis Weight	g/m <sup>2</sup>		70	80	90	100	110	115	120
Burst strength	kPa	ISO 2758	190	217	244	271	298	311	325
Tensile strength MD	kN/m	ISO 1924-3	4,5	5,1	5,8	6,4	7	7,4	7,7
Tensile strength CD	kN/m	ISO 1924-3	1,8	2	2,3	2,6	2,8	3	3,1
TEA MD	J/m <sup>2</sup>	ISO 1924-3	45	52	58	65	71	75	78
TEA CD	J/m <sup>2</sup>	ISO 1924-3	63	72	81	90	99	104	108
Tear strength MD	mN	ISO 1974	525	600	675	750	825	863	900
Tear strength CD	mN	ISO 1974	665	760	855	950	1045	1093	1140
Gurley	s	ISO 5636-5	45						
Cobb <sub>60</sub>	g/m <sup>2</sup>	ISO 535	30						
Moisture	%	ISO 287	7,8						

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.



Issued from 01.01.2021,  
latest version available on  
[www.mondigroup.com](http://www.mondigroup.com)

**Test conditions:**  
ISO 187:1990  
(23 C + 1 C/RH 50% +2)